



LORK INDUSTRIAS, S.L.
CARACAS, 11
08030—BARCELONA
SPAIN

Tel: +34 93 346 82 12
Fax: +34 93 311 30 60
Email: lork@lorkindustrias.com



DATA SHEET

FLEXOID

ALL PROPERTIES ARE BASED UPON 0.8 MATERIAL REFER TO ASTM F104 SECTION 7

PROPERTY	TEST METHOD	UNIT	VALUE
Max. Temperature		°C	120
Moisture Content	15 min / 100°C	%	8-14
Thickness	ASTMF104	mm	+/-10%
Compression	ASTMF36	%	25-40
Recovery	ASTMF36	%	40
Tensile Strength	ASTMF152	Mn/m ²	13.79
IRM 903 Oil Weight Increase	ASTMF146	%	15 max
IRM 903 Oil Thickness Increase	ASTMF146	%	5 max
Fuel B Weight Increase	ASTMF146	%	15 Max
Fuel B Thickness Increase	ASTMF146	%	5 max
Water Weight Increase	ASTMF146	%	90 max
Water Thickness Increase	ASTMF146	%	30 max